

**Inert Ceramic Balls**

Specification	Al ₂ O ₃ +SiO ₂ >92	Al ₂ O ₃ +SiO ₂ >91
Al ₂ O ₃	18-23%	23-30%
SiO ₂	72-74%	63-70%
Fe ₂ O ₃	<1.0%	<1.0%
MgO	<0.5%	<0.5%
CaO	<0.5%	<1.0%
K ₂ O+Na ₂ O	<2%	<2%
Shape	Sphere	Sphere
Water absorption	<0.3%	<0.3%
Hardness(MOHS)	6.5	7
Max operation Temp	980℃	1050℃
Alkali Resistance	>80%	>80%
Acid Resistance	>98%	>98%
Free Volume	40%	40%